


Technical Data Sheet



Federal Spec TTP-1952F Type I



Characteristics:

- ❖ Low VOC
- ❖ Lead and Chromate Free
- ❖ Excellent glass bead retention
- ❖ Non-flammable
- ❖ Non-bleeding
- ❖ Dry through in 2 hours maximum even at high humidity
- ❖ Spreading rate of 110 to 130 square feet per gallon
- ❖ Easy clean-up with soap and water
- ❖ Recommended for sealcoated surfaces, airfields, and highways
- ❖ 100% Acrylic Binder

Cautions:

- ❖ **CANNOT** be used in galvanized, brass, aluminum, or steel equipment – Recommend stainless steel or plastic components
- ❖ Keep from freezing
- ❖ Addition of water or other soluble solvents will adversely affect dry time
- ❖ All equipment should be cleaned before paint dries

Specifications

Viscosity:	80 – 90 Krebs Units	Total Solids:	77% Minimum
Weight per Gallon:	13.5 Minimum	Dry to NPU:	1 – 3 Minutes track free at 15 mils wet
Shelf Life:	1 Year Minimum Properly Stored	Vehicle Type:	100% Acrylic Fast release resin
Water Resistance:	2 hours minimum drying at temperatures above 50°F and humidity below 80% before exposure to moisture		