

# Technical Data Sheet



## Federal Spec. TTP-1952F Type III



### Characteristics:

- ❖ Low VOC
- ❖ Excellent initial and long term retroreflectivity (works best with big beads)
- ❖ Can be applied with standard waterborne striping equipment with no modifications
- ❖ Can be used to refurbish existing thermoplastic lines
- ❖ Lower cost than other durable products
- ❖ Excellent for crosswalks and legend markings
- ❖ Can be applied at films up to 30 mils wet without cracking
- ❖ 2 – 3 years durability
- ❖ Spreading rate of 180 to 200 linear feet per gallon of 4-inch line

### Cautions:

- ❖ **CANNOT** be used in galvanized, brass, aluminum, or steel equipment – Recommend stainless steel or plastic components
- ❖ Keep from freezing
- ❖ Addition of water or other soluble solvents will adversely affect dry time
- ❖ All equipment should be cleaned before paint dries

## Specifications

<b>Viscosity:</b>	80 – 90 Krebs Units	<b>Total Solids:</b>	75% Minimum
<b>Weight per Gallon:</b>	13.5 Minimum	<b>Volume Solids:</b>	60% Minimum
<b>Shelf Life:</b>	1 Year Minimum Properly Stored	<b>Vehicle Type:</b>	Patented crosslinking technology acrylic binder
<b>Dry to NPU:</b>	3 – 10 Minutes track free at 25 – 30 mils wet		